

Prodec 304L/4307

EN 1.4307, ASTM TYPE 304L / UNS S30403

General characteristics

A version of Core 304L/4307 with improved machinability. Improves productivity with faster machining, longer tool life, better dimensional tolerances, superior machined surface quality, and improved yields compared to conventionally produced Core 304L/4307.

Typical applications

- Fasteners
- Flanges
- Valves
- Pressure fittings

Products & dimensions

Quarto plate products, available dimensions (mm)

Surface finish		Coil / Strip		Plate / Sheet	
		Thickness	Width	Thickness	Width
1D	Hot rolled, heat treated, pickled			5.00-130.00	400-3200
1G	Ground			10.00-29.99	400-3200

Chemical composition

The typical chemical composition for this grade is given in the table below, together with composition limits given for the product according to different standards. The required standard will be fully met as specified on the order.

The chemical composition is given as % by mass.

	C	Mn	Cr	Ni	Mo	N	Other
Typical	0.02		18.1	8.1			
ASME II A SA-240	≤0.030	≤2.00	17.5-19.5	8.0-12.0		≤0.10	
ASTM A240	≤0.030	≤2.00	17.5-19.5	8.0-12.0		≤0.10	
ASTM A666	≤0.030	≤2.00	18.0-20.0	8.0-12.0		≤0.10	
EN 10028-7	≤0.030	≤2.00	17.5-19.5	8.0-10.5		≤0.10	
EN 10088-2	≤0.030	≤2.0	17.5-19.5	8.0-10.5		≤0.10	
EN 10088-3	≤0.030	≤2.00	17.5-19.5	8.0-10.5		≤0.10	

EN 10088-4	≤0.030	≤2.0	17.5-19.5	8.0-10.5		≤0.10	
IS 6911	≤0.030	≤2.00	17.5-19.5	8.0-12.0	≤0.70	≤0.10	
IS 6911	≤0.030	≤2.00	17.5-19.5	8.0-12.0	≤0.70	≤0.10	

Corrosion resistance

Pitting corrosion resistance		Crevice corrosion resistance
PRE	CPT	CCT
18	<10	<0

Pitting Resistance Equivalent (PRE) is calculated using the following formula: $PRE = \%Cr + 3.3 \times \%Mo + 16 \times \%N$
 Corrosion Pitting Temperature (CPT) as measured in the Avesta Cell (ASTM G 150), in a 1M NaCl solution (35,000 ppm or mg/l chloride ions).

Critical Crevice Corrosion Temperature (CCT) is obtained by laboratory tests according to ASTM G 48 Method F

For information on corrosion resistance properties in different environments, [use the online corrosion tables](#).

For more detailed information, please refer to the [Outokumpu Corrosion Handbook](#).

Mechanical properties

Cold rolled coil and sheet	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical (thickness 1 mm)	295	325	650	70				
ASME II A SA-240	≥ 170		≥ 485				≤ 201	
ASTM A240	≥ 170		≥ 485			≤ 92HRB	≤ 201	
EN 10028-7	≥ 220	≥ 250	520 - 700	≥ 45				
EN 10088-2	≥ 220	≥ 250	520 - 700	≥ 45				
EN 10088-4	≥ 220	≥ 250	520 - 700	≥ 45				
IS 6911	≥ 170		≥ 485			≤ 92HRB	≤ 201	
IS 6911	≥ 170		≥ 485			≤ 92HRB	≤ 201	

Hot rolled coil and sheet	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical (thickness 4 mm)	290	345	620	50			175	
ASME II A SA-240	≥ 170		≥ 485				≤ 201	
ASTM A240	≥ 170		≥ 485				≤ 201	
EN 10028-7	≥ 220	≥ 250	520 - 700	≥ 45				
EN 10088-2	≥ 220	≥ 250	520 - 700	≥ 45				
EN 10088-4	≥ 220	≥ 250	520 - 700	≥ 45				
IS 6911	≥ 170		≥ 485			≤ 92HRB	≤ 201	
IS 6911	≥ 170		≥ 485			≤ 92HRB	≤ 201	

Hot rolled quarto plate	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical (thickness 15 mm)	260	300	580	55				
ASME II A SA-240	≥ 170		≥ 485			≤ 92HRB	≤ 201	
ASTM A240	≥ 170		≥ 485			≤ 92HRB	≤ 201	
EN 10028-7	≥ 200	≥ 240	500 - 700	≥ 45				

EN 10088-2	≥ 200	≥ 240	500 - 700	≥ 45				
EN 10088-4	≥ 200	≥ 240	500 - 700	≥ 45				
IS 6911	≥ 170		≥ 485			≤ 92HRB	≤ 201	
IS 6911	≥ 170		≥ 485			≤ 92HRB	≤ 201	

Wire rod	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical	280	320	580	55				

¹⁾Elongation according to EN standard:

A₈₀ for thickness below 3 mm.

A for thickness = 3 mm.

Elongation according to ASTM standard A₂ or A₅₀.

Physical properties

Values according to EN 10088

Density kg/dm ³	Modulus of elasticity GPa	Thermal exp. at 100 °C 10 ⁻⁶ /°C	Thermal conductivity W/m°C	Thermal capacity J/kg°C	Electrical resistance μΩm	Magnetizable
7.9	200	16.0	15	500	0.73	No

Fabrication

More detailed information concerning welding procedures can be obtained from the Outokumpu Welding Handbook, available from our sales offices.

Standards & approvals

This grade is often double certified as EN 1.4301/1.4307, ASTM Type 304/304L.

Standard	Designation
ASME SA-240M Code Sect. II. Part A	TYPE 304L / UNS S30403
ASTM A240/A240M	TYPE 304L / UNS S30403
ASTM A666	TYPE 304L / UNS S30403
EN 10028-7, PED 2014/68/EU	1.4307
EN 10088-2	1.4307
EN 10088-3	1.4307
EN 10088-4	1.4307
IS 6911, AMENDMENT NO. 2	ISS 304 S2; ISS 304L

[Download Outokumpu manufacturing site certificates and approvals.](#)

Contacts & Enquiries

Contact your nearest sales office

www.outokumpu.com/contacts

Working towards forever.

We work with our customers and partners to create long lasting solutions for the tools of modern life and the world's most critical problems: Clean energy, clean water and efficient infrastructure. Because we believe in a world that lasts forever.

Information given in this brochure may be subject to alterations without notice. Care has been taken to ensure that the contents of this publication are accurate but Outokumpu and its affiliated companies do not accept responsibility for errors or for information which is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and Outokumpu and its affiliated companies accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability



outokumpu.com
steelfinder.outokumpu.com